

ICS 59.060.20
CCS W 52

FZ

**TEXTILE INDUSTRY STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

FZ/T 54044-2011

**Nylon 6 filament yarns for industry
(English Translation)**

Issued on: December 20, 2011

Implemented on: July 1, 2012

Issued by: Ministry of Industry and Information Technology of PRC

Table of Contents

Foreword...	3
1 Scope...	4
2 Normative references...	4
3 Terms and definitions...	5
4 Product identification...	5
5 Technical requirements...	5
6 Test methods...	6
7 Inspection rules...	9
8 Re-inspection rules...	10
9 Marking, packaging, transportation and storage...	11
Appendix A (Normative) Appearance requirements, inspection and assessment...	13

1 Scope

This standard specifies the terms and definitions, product identification, technical requirements, test methods, inspection rules, marking, packaging, transportation and storage requirements for nylon 6 filament yarn for industry.

This standard applies to filament yarns for industry use, which are made from nylon 6 chips. This product is mainly used for rubber tires, conveyor belts, canvas, ropes, fishing nets, etc. after post-processing. Its linear density range is 930 dtex~2100 dtex.

For other specifications of products, this standard can be used for reference.

2 Normative references

The following documents are essential for the application of this document. For referenced documents with dates, only the versions corresponding to the dates are applicable to this document; for referenced documents without dates, the latest versions (including all amendments) are applicable to this document.

GB/T 2828.1-2003 Sampling procedures for inspection by attributes - Part 1:

Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection

GB/T 3291.1 Textiles - Terms of textile material properties and test - Part 1: Fibre and yarn

GB/T 3291.3 Textiles - Terms of textile material properties and test - Part 3:

General

GB/T 4146.1 Textiles - Man-made fibres - Part 1: Generic names

GB/T 6502 Sampling method of man-made filament yarns

GB/T 6503 Man-made fibres - Test method of moisture regain

GB/T 6529 Textiles - Standard atmospheres for conditioning and testing

GB/T 8170 Rules of rounding off for numerical values & expression and judgment of limiting values

GB/T 14343 Testing method for linear density of man-made filament yarns

Si -- dry heat shrinkage of each sample, %;

n -- the total number of tests.

6.4.5 Rounding of data

The test results are rounded to one decimal place in accordance with the provisions of GB/T 8170.

6.5 Test for strength retention rate at high temperature

It is determined by negotiation between the supply and demand parties, or implemented in accordance with Appendix B.

6.6 Moisture regain

The test shall be implemented in accordance with the provisions of GB/T 6503.

6.7 Appearance inspection

The inspection shall be implemented as agreed upon by the supply and demand parties or in accordance with the provisions of Appendix A.

7.1 Inspection types

All items in Table 1 are factory inspection items.

7.2 Inspection items

7.2.1

Appearance inspection items shall be inspected according to the requirements of the supplier and the buyer or according to the requirements specified in Table A.1.

7.2.2

The physical properties shall be in accordance with the requirements of Table 1 and tested according to the test methods specified in this standard.

7.2.3

The strength retention rate at high temperature shall comply with the requirements of 5.3 and be tested according to the test methods specified in this standard.

7.3 Batching rules

Periodic sampling is adopted within a certain range to form a test lot. A product lot can be composed of one test lot or several test lots.

7.4 Sampling regulations

7.4.1

All appearance items shall be inspected.

7.4.2

The laboratory samples for physical property tests shall be in accordance with

GB/T 6502. The appearance and roll weight of the laboratory samples shall conform to the corresponding grades.

7.4.3

Damaged rolls shall not be sampled.

7.5 Comprehensive assessment

7.5.1

The appearance inspection items shall be evaluated roll by roll according to the requirements of the supplier and the buyer or as specified in Table A.1.

7.5.2 Under the condition of qualified appearance quality, the test values or calculated

values of the physical property items shall be compared with the index limit values in

Table 1 according to the rounded value comparison method in GB/T 8170, and the lowest grade in the property items in the test lot shall be determined as the grade of the product lot.

7.5.3 If the user has special requirements for property indicators, the classification regulations shall be implemented in accordance with the contract standards.

8.1 General

Within three months after a batch of products arrives at the consignee, a re-inspection may be requested for acceptance or if there is any objection to the quality. If more than one-third of the batch of products has been used, re-inspection may not be requested. If the quality of the batch of products affects the quality of the subsequently processed products and causes serious losses, the supply and demand parties shall analyze the reasons, clarify the responsibilities, and negotiate a solution.

8.2 Inspection items

Same as 7.2.

8.3 Batching rules

Batches are grouped according to product lots.

8.4 Sampling regulations

8.4.1

Appearance is inspected by sampling. The sample size (code) is determined according to the batch size and the general inspection level II in Table 1 of GB/T

2828.1-2003.

8.4.2

Laboratory samples for physical property test items shall be sampled and tested in accordance with the provisions of 7.4.2.

8.5 Evaluation of test results

8.5.1

For appearance, according to the sample size in 8.4.1, and the acceptable quality level AQL value of 4.0 for "normal inspection single sampling plan" in Table 2-A of

GB/T 2828.1-2003, determine the qualified acceptance number A_c and the unqualified rejection number R_e . Evaluate according to the provisions of 5.4; when the number of unqualified rolls is $\leq A_c$, it is judged as the original grade; when the number of unqualified rolls is $\geq R_e$, it is judged as not meeting the original grade.

8.5.2

Physical property indicators shall be evaluated in accordance with 7.5.2; if they are higher than or equal to the original grade, they shall be judged as conforming; if they are lower than the original grade, they shall be judged as non-conforming.