

ICS 27.120.30

CCS F46



**NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

GB/T 11848.8-2025

Replacing GB/T 11848.8-1989

**Methods for analysis of uranium ore concentrate - Part 8:
Determination of moisture - Gravimetric method**

铀矿石浓缩物分析方法 第8部分：水分的测定 重量法

Issued on: October 5, 2025

Implemented on: May 1, 2026

**Issued by: State Administration for Market Regulation;
Standardization Administration of China**

Table of Contents

- 1 Scope
- 2 Normative references
- 3 Terms and Definitions
- 6 Instruments and Equipment
- 6.2 Electronic balance, with a graduation value of
- 8 Determination of Moisture Content by Gravimetric Method Warning

Foreword

This document complies with the provisions of GB/T 1.1-2020 "Standardization Work Guidelines Part

1. Structure and Drafting Rules of Standardization Documents". Drafting. This document is Part 8 of GB/T 11848, "Analytical Methods for Uranium Ore Concentrates". GB/T 11848 has the following parts published.

- 1. Determination of Uranium by Ferrous Sulfate Reduction-Potassium Dichromate Titration;
- 2. Determination of Nitric Acid-Insoluble Uranium by Spectrophotometry;
- 3. Gravimetric determination of extractable organic compounds;
- 4. Determination of Arsenic and Mercury by Hydride Generation-Atomic Fluorescence Spectrometry;
- 5. Determination of Carbonate by Infrared Absorption Method;
- 6. Determination of Fluorine by Ion-Selective Electrode Method.
- 7. Determination of Halogens - Volhard Method;
- 8. Determination of Moisture Content by Gravimetric Method;
- 9. Determination of Silicon by Spectrophotometry;
- 10. Determination of Sulfur by Infrared Absorption Spectroscopy;
- 11. Determination of Thorium by Inductively Coupled Plasma Mass Spectrometry;
- 12. Determination of Boron by Inductively Coupled Plasma Mass Spectrometry;

1 Scope

GB/T 11848.8-2025 is the Chinese national standard on methods for analysis of uranium ore concentrate - part 8: determination of moisture - gravimetric method, in the field of energy and heat transfer engineering. The /T suffix marks it as a recommended standard: it is not compulsory by itself, but it becomes binding as soon as a contract, a tender or a customer specification calls it up - which in practice is how most foreign buyers meet it. It was issued on 5 October 2025 by the State Administration for Market Regulation; Standardization Administration of China, and has been in force since 1 May 2026. Classification: ICS 27.120.30, CCS F46. This page is published from the official record of the standard held by the Chinese standards administration: the identification, the dates, the classification and the issuing body are taken from there. The clause text, the tables and the numeric limits are in the document itself, which is delivered complete in English translation.

This document describes a method for determining the moisture content in uranium ore concentrates. This document applies to the determination of moisture content in uranium ore concentrates.

2 Normative references

The contents of the following documents, through normative references within the text, constitute essential provisions of this document. Dated citations are not included. For references to documents, only the version corresponding to that date applies to this document; for undated references, the latest version (including all amendments) applies. This document.

GB/T 10268 Uranium Ore Concentrates

3 Terms and Definitions

The terms and definitions defined in GB/T 10268 apply to this document.

4.Principles The sample was dried at 110°C for 24 hours, cooled, and weighed. After constant weight, the moisture content was calculated based on the mass loss.

5.Reagents or materials Color-changing silica gel or other desiccants.

6 Instruments and Equipment

6.1 Electric heating constant temperature chamber, 10°C~250°C.

6.2 Electronic balance, with a graduation value of

0.1 mg.

6.3 Electronic balance, maximum weighing capacity 3000g, scale division value 0.5g.

6.4 Desiccator, place dried color-changing silica gel or other desiccant inside.

6.5 Weighing bottle with cap, 50mm in diameter and 30mm in height, dried at $110^{\circ}\text{C}\pm 2^{\circ}\text{C}$ and weighed to constant weight before use.

8 Determination of Moisture Content by Gravimetric Method Warning

---Personnel using this document should have practical experience working in a formal laboratory. This document does not cover all possible safety issues. Users are responsible for taking appropriate safety and health measures and ensuring compliance with relevant national regulations. This document covers the following. Toxic and hazardous waste should be collected and stored centrally, and all types of waste should be managed responsibly in strict accordance with the relevant regulations and technical standards of the national environmental protection administration. Centralized processing.