

ICS 79.060.20  
CCS B 70



**NATIONAL STANDARD OF THE  
PEOPLE'S REPUBLIC OF CHINA**

**GB/T 12626.9-2015**

26.9-1990; GB/T 12626.8-1990; GB/T 12626.7-1990; GB/T 12626.6-1990; GB/T 12626.5-1990; GB/T 12626.4-1990

---

**Hard fibreboard -- Part 9: Load bearing boards for use in humid  
conditions**

湿法硬质纤维板 第9部分：潮湿条件下使用的承载用板

**(English Translation)**

**Issued on: July 3, 2015**

**Implemented on: November 2, 2015**

---

**Issued by: Standardization Administration of China**

## Table of Contents

- Foreword
- 1 Scope
- 2 Normative references
- 3 Requirements
- 4.1 Sampling and specimen size

### Foreword

GB/T 12626 "wet hardboard" is divided into nine sections.

- Part 1. Definitions and classification;
- Part 2. Common requirements for all board types;
- Part 3. Specimen Samples and measurements;
- Part 4. General plate for use in dry conditions;
- Part 5. Common plate under wet conditions of use;
- Part 6. ordinary plate under high humidity conditions of use;
- Ordinary plate under outdoor conditions of use;. --- Part 7
- Part 8. under dry conditions using carrier plate;
- Part 9. humid conditions bearing plate used.

This section GB/T Part of 912,626.

This section drafted in accordance with GB/T 1.1-2009 given rules.

This is Part instead of GB/T 12626.4 ~ 12626.9-1990 in content.

This section uses redrafted reference method ISO 27769-2:2009 "Wet wood-based panels Fiberboard - Part 2. Requirements" the preparation, and ISO 27769-2:2009 is not equivalent degree of consistency. Physical and mechanical properties of this part and ISO 27769-2:2009 in Hard Under wet conditions Fibreboard part carrier plate using technical requirements consistent.

Please note that some of the content of this document may involve patents. Release mechanism of the present document does not assume responsibility for the identification of these patents.

This part by the State Forestry Administration.

This part of the man-made board by the National Standardization Technical Committee (SAC/TC198) centralized.

This section drafted by. China Forestry Science Institute of Wood Industry, Xinxiang City Xin Wood Co. Tyrone, Dunhua Dan Fenglin Fiberboard industry limited liability company, Yichun City, Heilongjiang Province friendship fibreboard plant.

## 1 Scope

This section GB/T 12626 specifies the carrier plate in humid conditions of use requirements, test methods, inspection rules and signs, including Loading, transport and storage.

This section applies to GB/T defined in 3.1 wet hardboard 12626.1-2009.

## 2 Normative references

The following documents for the application of this document is essential. For dated references, only the dated version suitable for use herein Member. For undated references, the latest edition (including any amendments) applies to this document.

GB/T 12626.1-2009 wet hardboard Part 1. Definitions and classification GB/T  
12626.2-2009 wet hardboard Part 2. Common requirements for all board types GB/T  
12626.3-2009 wet hardboard Part 3. Specimen Samples and measurements GB/T  
17657-2013 panels and veneer plywood physical and chemical performance test method

## 3 Requirements

Common indicators 3.1 thickness deviation, length and width of the deviation should be consistent with GB/T 12626.2-2009 requirements.

### 3.2

physical and mechanical properties are shown in Table 1.

Table 1 physical and mechanical properties

Property Unit

Basic thickness  $t$ /mm  $t \leq 3.5$  3.5  $3.5 < t \leq 5.5$  5.5 MOR MPa 38 34 32 Modulus of elasticity MPa 3700 3100 2900 Internal bond strength MPa 0.80 0.70 0.65 24h thickness swelling% 171 512 Moisture resistant Select 1. 2h boiling water boiled internal bond strength Option 2. After 70 °C water immersion MOR MPa MPa 0.40 0.35 0.32

**NOTE:** bending strength, elastic modulus, internal bond strength, internal bond strength after boiling water boiled 2h and 70 °C water immersion MOR for the lower specification limit, 24h water

Thickness swelling of the specification limits.

Test Method 4

#### **4.1 Sampling and specimen size**

Conducted in accordance with GB/T 12626.3-2009 in Chapter 3 and Chapter 4.