



**NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

GB/T 2652-2022

**Destructive tests on welds in metallic materials - Longitudinal
tensile test on weld metal in fusion welded joints**

Issued on: October 12, 2022

Implemented on: October 12, 2022

Issued by: SAMR; SAC

Table of Contents

Foreword...	3
1 Scope...	5
2 Normative References...	5
3 Terms and Definitions...	5
4 Symbols and Abbreviations...	5
5 General...	6
6 Preparation of Specimen...	6
6.1 Sampling location...	6
6.2 Marking...	6
6.3 Heat treatment and/or aging...	6
6.4 Sampling...	6
6.5 Specimen processing...	7
6.6 Dimensions...	8
6.7 Surface quality...	9
7 Test Procedure...	9
8 Test Results...	9
8.1 General requirements...	9
8.2 Fracture surface inspection...	9
9 Test Report...	9
Appendix A (Informative) Example of Test Report...	11

Foreword

This Document was drafted as per the rules specified in GB/T 1.1-2020 Directives for Standardization - Part 1: Rules for the Structure and Drafting of Standardizing Documents.

This Document replaced GB/T 2652-2008 Tensile Test Methods on Weld and Deposited Metal.

Compared with GB/T 2652-2008, the major technical changes of this Document are as follows

besides the structural adjustments and editorial modifications:

--- Change the requirements of "Scope" (see Clause 1 of this Document, Clause 1 of the

2008 Edition);

--- Add the requirements for continuously increasing the test force (see Clause 5 of this

Edition);

--- Add marking requirements (see 6.2 of this Edition);

--- Change the processing requirements of "other metal materials" (see 6.4.3 of this Edition;

5.4.3 of the 2008 Edition);

--- Change the tolerance requirements of the surface quality of the specimen (see 6.7 of this

Edition; 5.5.1, 5.7 of the 2008 Edition);

--- Change the requirements for test report (see Clause 9 of this Edition; Clause 8 of the

2008 Edition).

This Document equivalently adopts ISO 5178:2019 Destructive Tests on Welds in Metallic Materials - Longitudinal Tensile Test on Weld Metal in Fusion Welded Joints.

Please note some contents of this Document may involve patents. The issuing agency of this

Document shall not assume the responsibility to identify these patents.

This Document was proposed by China Machinery Industry Federation.

This Document shall be under the jurisdiction of National Technical Committee on Welding of

Standardization Administration of China (SAC/TC 55).

Drafting organizations of this Document: Shanghai Research Institute of Materials; Harbin

Welding Institute Co., Ltd.; Baoji Petroleum Steel Pipe Co., Ltd.; Xiamen Chengcan Industrial

Equipment Co., Ltd.; Shenzhen Jinbofang Laser Technology Co., Ltd.; Shanghai Institute of

Special Equipment Inspection and Technical Research; Jiangsu Province Special Equipment

Safety Supervision and Inspection Institute; China Machine Intelligent Equipment Innovation

Research Institute (Ningbo) Co., Ltd.; Taiyuan Heavy Industry Co., Ltd.; and Guangdong

Foreweld Co., Ltd.

Chief drafting staffs of this Document: Zhai Lianna, Chen Mo, Wang Bin, Bi Zongyue, Wang

Destructive Tests on Welds in Metallic Materials -

Longitudinal Tensile Test on Weld Metal in Fusion Welded

Joints

1 Scope

This Document specifies the specimen dimensions and test procedure for the longitudinal tensile test of circular cross-section specimens of fusion welded joint weld metal to determine

its mechanical properties.

This Document is applicable to all kinds of metal material products manufactured by fusion welding methods and whose joint dimensions can be made into circular cross-section specimens

according to ISO 6892-1.

2 Normative References

The provisions in following documents become the essential provisions of this Document through reference in this Document. For the dated documents, only the versions with the dates

indicated are applicable to this Document; for the undated documents, only the latest version

(including all the amendments) is applicable to this Document.

ISO 6892-1 Metallic Materials - Tensile Testing - Part 1: Method of Test at Room Temperature

NOTE: GB/T 228.1-2021 Metallic Materials - Tensile Testing - Part 1: Method of Test at Room

Temperature (ISO 6892-1:2019, MOD)

3 Terms and Definitions

For the purposes of this Document, there are no terms and definitions apply.

4 Symbols and Abbreviations

The symbols and abbreviations used in the longitudinal tensile test shall be in accordance with

the provisions of ISO 6892-1.

machine.

6.7 Surface quality

The specimen tolerance shall comply with the provisions of ISO 6892-1.

Specimens shall be free from strain hardening or overheating.

7 Test Procedure

The test force shall be applied to the specimen in a continuous and gradual manner according

to the provisions of ISO 6892-1.

8.1 General requirements

The test results shall be determined in accordance with the provisions of ISO 6892-1.

8.2 Fracture surface inspection

After the specimen breaks, the surface of the fracture shall be inspected; and any flaws on the

fracture that may adversely affect the test shall be recorded in the report, including the type, size and quantity of the flaws. If white spots appear, they shall be recorded and only the central

area of the white spots shall be considered as a flaw.

9 Test Report

In addition to the content required by ISO 6892-1, the test report shall also include the following

content:

- a) The reference number of this Document, such as GB/T 2652-2022;
- b) The location of the specimen, if necessary, attach a schematic diagram (see Figures 1 and