

ICS 29.060
CCS K 13



**NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

GB/T 2951.31-2008

Replacing GB/T 2951.6-1997

Common test methods for insulating and sheathing materials of electric and optical cables -- Part 31: Methods specific to PVC compounds -- Pressure test at high temperature -- Test for resistance to cracking

电缆和光缆绝缘和护套材料通用试验方法 第31部分：聚氯乙烯混合料专用试验方法 高温压力试验 抗开裂试验

(English Translation)

Issued on: June 26, 2008

Implemented on: April 1, 2009

Issued by: Standardization Administration of China

Table of Contents

Foreword
1 Overview
1.1 Scope
1.2 Normative references
3 Scope
4 Type tests and other tests
5 Pretreatment
6 Temperature test
7 Intermediate value

Foreword

GB/T 2951 "cable and the cable Common test methods for insulating and sheathing materials" is divided into 10 parts.

--- Part 11. General test methods for measuring the thickness and overall dimensions --- mechanical tests;

--- Part 12. Common test methods --- Thermal aging methods;

--- Part 13. General test method for determining the density method --- Water absorption tests - Shrinkage test;

--- Part 14. Common test methods --- low temperature test;

--- Part 21. elastomeric compounds specific test method Ozone resistance --- Hot set test - Mineral oil immersion test;

--- Part 31. Methods specific to PVC compounds - Pressure test --- high temperature resistance to cracking;

--- Part 32. Methods specific to PVC compounds - Loss of mass test --- thermal stability test;

--- Part 41. polyethylene and polypropylene compounds - Test methods --- ESCR test melt index measurement Measurement Method --- direct combustion of polyethylene in carbon black and/or mineral filler content --- thermal gravimetric analysis (TGA) measurements of carbon Black --- microscopy to assess the content of carbon black dispersion in polyethylene;

--- Part 42. polyethylene and polypropylene compounds - Test methods --- After heat treatment the tensile strength and elongation at break test Increase the quality of experience --- --- winding test air test after thermal aging was measured after heat treatment --- --- long-term thermal stability Qualitative tests --- copper-catalyzed oxidative degradation test methods;

--- Part 51. Methods specific to filling compounds - Drop point --- --- oil separator temperature brittleness --- --- total acid corrosion this part of the National Standardization Technical Committee of wire and cable.

This section is drafted. Shanghai Electric Cable Research Institute.

1.1 Scope

GB/T 2951 provides power distribution and communication cables and fiber optic cable, including marine and offshore cables and cable insulation and jacketing polymer Test methods for materials.

This section GB/T 2951 specifies the high temperature pressure test methods and test methods for resistance to cracking. For wire, cable and optical fiber poly Vinyl chloride insulation and sheathing materials.

1.2 Normative references

The following documents contain provisions which, through reference to GB/T 2951 to the present, constitute provisions of this section. For dated references Documents, all subsequent amendments (not including errata content) or revisions do not apply to this section, however, encourage the present section Research on the parties to reach an agreement to use the latest versions of these documents. For undated references, the latest edition of in this section.

GB/T 2951.11-2008 cable and the cable Common test methods for insulating and sheathing materials - Part 11. General test side Law --- --- Measurement of thickness and overall dimensions of mechanical tests (IEC 60811-1-1:1993, IDT) Test Principle 2 this section does not provide all of the test conditions (such as temperature, duration, etc.) as well as all of the test requirements, they should be on cable Product standards to be defined.

Any test requirements specified in this standard can be modified in the relevant product standard cable in order to meet the needs of a particular type of cable.

3 Scope

Test conditions and test parameters specified in this section apply to the cable, the most common type of cable, wires and cords insulation and sheathing materials.

4 Type tests and other tests

Test methods described in this section is first used as a type test. Some pilot projects to test its type testing and regular of (Such as routine test) conditions are fundamentally different, this section has been pointed out these differences.

5 Pretreatment

All tests shall be insulated and sheath material extruded or vulcanized (or crosslinking) after storage for at least 16h before proceeding.

6 Temperature test

Unless otherwise specified, the tests should be carried out at ambient temperature.

7 Intermediate value

When the test data obtained proper number in ascending or descending order, if the number of valid data is odd, the median is positive A middle value; if even, the median is the average of the middle two values.

GB/T 2951.31-2008/IEC 60811-3-1. 1985