

ICS 31.030
CCS L 90



**NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

GB/T 45505.5-2025

**Test method of flat panel display glass substrate - Part 5:
Photoelectric performance**

平板显示器基板玻璃测试方法 第5部分：光电性能

Issued on: August 1, 2025

Implemented on: February 1, 2026

**Issued by: State Administration for Market Regulation;
Standardization Administration of the PRC**

Table of Contents

Foreword

Introduction

1 Scope

2 Normative references

3 Terms and Definitions

4 Test Environment

5 Test methods

5.1 Transmittance

5.1.1 Test principle

5.1.2 Test apparatus

Foreword

This document is in accordance with the provisions of GB/T 1.1-2020 "Guidelines for standardization work Part 1: Structure and drafting rules for standardization documents" Drafting.

This document is Part 5 of GB/T 45505 "Test methods for glass substrates for flat panel displays". Lower part.

- Part 1: Appearance and geometric dimensions;
- Part 2: Surface properties;
- Part 3: Thermal properties;
- Part 4: Mechanical properties;
- Part 5: Optoelectronic properties.

Please note that some of the contents of this document may involve patents. The issuing organization of this document does not assume the responsibility for identifying patents.

This document was proposed and coordinated by the National Technical Committee for Semiconductor Equipment and Materials Standardization (SAC/TC203).

This document was drafted by: IRICO Group Co., Ltd., China Electronics Technology Standardization Institute, IRICO Display Devices Co., Ltd., Hebei Guangxing Semiconductor Technology Co., Ltd., Bengbu Zhongguang Technology Co., Ltd., Rainbow Group (Shaoyang) Special Glass Co., Ltd., Shijiazhuang Xuxin Optoelectronics Technology

Co., Ltd., Hunan Shaohong Special Glass Co., Ltd., Zhengzhou Xuifei Optoelectronics Technology Co., Ltd., China Building Material Glass New Materials Research Institute Group Co., Ltd., Gansu Xusheng Display Technology Co., Ltd., Wuhu Dongxu Optoelectronics Technology Co., Ltd., Zhejiang Chuangrou Display Technology Technology Co., Ltd., Dongxu Group Co., Ltd., Xinjiang Tengyu Optoelectronics Technology Co., Ltd., Wuhan Jingce Electronics Group Co., Ltd., Shenzhen Ruiou Optical Co., Ltd., Shenzhen Guoxian Technology Co., Ltd., Shenzhen Yurong Technology Co., Ltd., Qingdao Fusion Optoelectronics Technology Co., Ltd.

Company, Zhejiang Baotai Electronics Co., Ltd., Zhejiang Xingke Optoelectronics Technology Co., Ltd.

The main drafters of this document are: Chen Xiaoning, Yang Guohong, Wu Yiran, Li Qing, Zhao Junsha, Li Miao, Cao Zhiqiang, Wu Xiaoxi, Cao Kewei, Xu Lihua, Hu Hengguang, Jin Liangmao, Yang Rong, Gao Yu, Xue Xinjian, Shen Yuguo, Shi Zhiqiang, Li Jingbo, Liu Zhengmao, Liu Jun, Jiang Zhiwen, Shi Zeyuan, Zhang Xiaochun, Zhang Baoshuai, Zhu Mingliu, Cao Xin, Zhang Yujiao, Li Heran, He Huaisheng, Zheng Quan, Wang Shilan, Shi Lifan, Li Ruijiao, Si Yanyang, Yao Wenlong, Su Jihua, Zhang Wenliang, Cui Jiedong, Yang Yi, Zhang Zhanyong, Ni Jia, Wei Zeguangu, Hu Wentao, Liu Ronghua, Du Qing, Ou Mulan, Fang Xuesen, Zheng Pan, Yang Daohui, and Zhang Pan.

Introduction

Flat panel display substrate glass is a key strategic material in the electronic information display industry. The quality of substrate glass is closely related to the resolution and transparency of the finished panel.

Brightness, thickness, weight, viewing angle and other indicators are closely related, representing the highest level in the field of modern glass large-scale manufacturing in the world.

As substrate glass continues to become higher definition, larger size, and ultra-thin, the quality requirements for display substrate glass are increasing year by year.

Appearance, length and width dimensions and deviations, thickness deviation, thickness difference, edge shape, cutting angle deviation, positioning angle deviation, right angle, deflection, warping, Surface roughness, waviness, annealing point, strain point, softening point, average linear thermal expansion coefficient, thermal conductivity, reheat linear shrinkage, density, stress, Young's modulus, shear modulus, Poisson's ratio, Vickers hardness, transmittance, refractive index, volume resistivity, dielectric constant and dielectric loss factor are for flat plates.

These indicators will affect the product quality of flat panel display substrate glass, so it is necessary to establish the Test methods for display substrate glass.

GB/T 45505 aims to provide test methods for various properties of flat panel display substrate glass and is intended to consist of five parts.

- Part 1: Appearance and geometric dimensions. The purpose is to provide test methods for the appearance and geometric dimensions of flat panel display substrate glass.
- Part 2: Surface properties. The purpose is to provide a test method for the surface properties of flat panel display substrate glass.
- Part 3: Thermal properties. The purpose is to provide a test method for the thermal properties of flat panel display substrate glass.
- Part 4: Mechanical properties. The purpose is to provide test methods for the mechanical properties of flat panel display substrate glass.
- Part 5: Photoelectric properties. The purpose is to provide test methods for the photoelectric properties of flat panel display substrate glass.

Test methods for flat panel display substrate glass Part 5: Optoelectronic properties

1 Scope

This document describes the test methods for transmittance, refractive index, volume resistivity, dielectric constant, and dielectric loss factor of flat panel display substrate glass. method.

This document applies to the testing of substrate glass for flat panel displays.

2 Normative references

GB/T 10580-2015

GB/T 26810

GB/T 31838.6-2021

GB/T 32639

3 Terms and Definitions

The terms and definitions defined in GB/T 32639 apply to this document.

4 Test Environment

Unless otherwise specified, the tests should be carried out under the following environmental conditions.

- a) Temperature. $25^{\circ}\text{C} \pm 5^{\circ}\text{C}$.

b) Relative humidity. 40%~70%.

5.1.1 Test principle

Use visible light spectrophotometer to test the transmittance within the specified wavelength range. When light is incident vertically on a transparent object, the difference between the transmitted light and the incident light is The ratio of the luminous flux is the transmittance of the sample. The transmittance of the sample is different at different wavelengths.

5.1.2 Test apparatus

The performance of the visible spectrophotometer shall comply with the requirements specified in GB/T 26810. It shall also meet the following requirements.