

ICS 77.120.30

CCS H 13



**NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

GB/T 5121.16-2008

Replacing GB/T 5121.16-1996; GB/T 13293.3-1991

**Methods for chemical analysis of copper and copper alloys --
Part 16: Determination of chromium content**

铜及铜合金化学分析方法 第16部分：铬含量的测定

(English Translation)

Issued on: June 17, 2008

Implemented on: December 1, 2008

Issued by: Standardization Administration of China

Table of Contents

What this standard covers	1
Document data	2

What this standard covers

This standard specifies the method for determination of copper and copper alloy chromium content. This method is suitable for the determination of copper and copper alloy chromium content. Measuring range: 0. 00005% to 0. 0010%. Method 2 flame atomic absorption spectrometry method provides for the determination of copper and copper alloy chromium content. This method is suitable for the determination of copper and copper alloy chromium content. Measuring range: 0. 050% to 1. 30%. The total chromium alloy chromium content-Determination of copper in the international standards set out by titration Titration Method 3 This method requirements. This method is suitable for the chromium content of 0. 10% to 2. 0% of the product.

Document data

International classification (ICS): 77.120.30.

Chinese classification (CCS): H13.

Estimated length of the Chinese original: 13,114 words.

Adopted international standard: ISO 6437-1984, MOD; ISO 4744-1984, MOD.

Supersedes the earlier edition GB/T 5121.16-1996; GB/T 13293.3-1991.