

ICS 71.100.40
CCS E 30



**NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

GB/T 5816-1995

Replacing GB/T 5816-1986

**Catalysts and adsorbents. Determination of surface area
(English Translation)**

Issued on: December 21, 1995

Implemented on: August 1, 1996

Issued by: State Bureau of Technical Supervision

Table of Contents

What this standard covers	1
Document data	2

What this standard covers

This standard specifies the determination of nitrogen adsorption by static volumetric method of catalyst surface area of the adsorbent. This standard applies with type ? or ? type adsorption isotherms, surface area greater than $1\text{m}^2/\text{g}$ catalyst, adsorbent.

Document data

International classification (ICS): 71.100.40.

Chinese classification (CCS): E30.

Estimated length of the Chinese original: 3,362 words.

Adopted international standard: ASTM D3663-1992, NEQ.

Supersedes the earlier edition GB/T 5816-1986.