

ICS 25.220.20

CCS H 20



**NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

GB/T 8752-2006

Replacing GB/T 8752-1988

**Anodizing of aluminium and its alloys -- Check of continuity of
thin anodic oxide coating -- Copper sulphate test**

铝及铝合金阳极氧化 薄阳极氧化膜连续性检验方法 硫酸铜法

(English Translation)

Issued on: September 26, 2006

Implemented on: February 1, 2007

**Issued by: General Administration of Quality Supervision, Inspection and
Quarantine of the People's Republic of China, Standardization
Administration of the People's Republic of China**

Table of Contents

What this standard covers	1
Document data	2

What this standard covers

This standard specifies the test with a copper sulfate solution anodized aluminum and aluminum alloy thin film continuity approach. This standard applies to thin anodized aluminum and aluminum alloy film (thickness less than 5 μm) rapid test continuity. When the anodic oxide film on the visible surface defects doubt there between, the present method can be used to determine whether the defect is a partial block bare base metal trap.

Document data

International classification (ICS): 25.220.20.

Chinese classification (CCS): H20.

Estimated length of the Chinese original: 6,613 words.

Adopted international standard: ISO 2085-1976, MOD; EN 12373.16-2001, NEQ.

Supersedes the earlier edition GB/T 8752-1988.