

ICS 75.100
CCS E 36

SH

**INDUSTRY STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

SH/T 0790-2007

**Standard test method for oxidation induction time of lubricating
greases by pressure differential scanning calorimetry**

润滑脂氧化诱导期测定法(压力差示扫描量热法)

(English Translation)

Issued on: August 1, 2007

Implemented on: January 1, 2008

Issued by: Ministry of Industry and Information Technology

Table of Contents

What this standard covers	1
Document data	2
Standards quoted by this document	3

What this standard covers

This standard specifies a pressure differential scanning calorimetry grease oxidation induction period, the oxygen pressure of 3. 5MPa, temperature between 155°C ~ 210°C.

Document data

International classification (ICS): 75.100.

Chinese classification (CCS): E36.

Estimated length of the Chinese original: 9,978 words.

Adopted international standard: ASTM D 5483-2002, MOD.

Standards quoted by this document

ASTM E473