

ICS 73.080
CCS D 52

YB

**INDUSTRY STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA**

YB/T 6040-2022

**Fluorite pellets - Method for determination of drop strength
(English Translation)**

Issued on: September 30, 2022

Implemented on: April 1, 2023

Issued by: Ministry of Industry and Information Technology

Table of Contents

What this standard covers	1
Document data	2

What this standard covers

This standard specifies the method for the determination of the drop strength of fluorite pellets. This standard applies to fluorite pellets. This standard uses artificial simulation of certain experimental conditions to measure the crushing of samples dropped from high places. The principle is: drop a certain amount of fluorite pellets freely from a specified height onto a steel plate with a specified thickness, and express the drop strength by the mass percentage of fluorite pellets with a particle size greater than 10mm in the original fluorite pellet sample.

Document data

International classification (ICS): 73.080.

Chinese classification (CCS): D52.

Estimated length of the Chinese original: 6,682 words.